

844WB Liquid



Translucent ESD Coating

844WB is a one-part, translucent, water-based ESD paint made from a high quality aliphatic polyester urethane latex. It adheres strongly to plastics, paints, metals, and many other surfaces. The cured coating is flexible, durable, and will not crack, chip or peel.

This non-flammable, low odor, low VOC coating is used in electronic assembly lines to protect against electrostatic charge build-up on tools, production conveyor and bumpers, assembly trays, workstation surfaces, and enclosures.

844WB can be applied by roller, brush, manual and selective spray equipment.



Features & Benefits

- Permanent static dissipative coating
- Non-flammable, low odor, and low VOC
- Ready to spray
- Meets ANSI/ESD-S20.20
- Reworkable
- Strong adhesion with excellent flexibility

Available Packaging

Cat. No.	Packaging	Net Vol.	Net Wt.
844WB-850ML	Can	850 mL	878 g
844WB-3.6L	Can	3.60 L	3.72 kg

Contact Information

MG Chemicals, 1210 Corporate Drive
Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772

International: +(1) 905-331-1396

Europe: +(44)1663 362888

Cured Properties

Surface Resistance @ 50 μm	$5.6 \times 10^7 \Omega/\text{sq}$
Service Temperature Range	-40–120 °C

Usage Parameters

Recoat Time	5 min
Cure Times	45 min @ 45 °C 30 min @ 65 °C 10 min @ 80 °C
Recommended Film Thickness	50 μm
Minimum Film Thickness	40 μm
Theoretical Coverage @ 2 mil	36 000 cm^2/L

Uncured Properties

Viscosity @ 25 °C	128 cP
Density	1.0 g/mL
Percent Solids	29 %
Shelf Life	2 y
Calculated VOC	71.3 g/L

844WB Liquid



Application Instructions

Read the product SDS before using this product (downloadable at www.mgchemicals.com).

Recommended Preparation

Plastic—Clean the substrate with Isopropyl Alcohol, MG #824, so the surface is free of oils, dust, and other residues.

Drywall—For new drywall, apply directly on top of the drywall primer, after the primer has properly cured. When applying on top of existing paint, first wash the wall with a solution of T.S.P. diluted with water at a 1:10 ratio, to ensure good adhesion.

Prior to each use, stir the contents in the container until homogenous or use a paint shaker if available.

Paint Roller

This product may be applied with a standard paint roller. Thinning is not required.

Manual Spray Guns

Use a standard fluid nozzle gun to spray the diluted paint. The settings listed below are recommendations; however, performance will vary with different brands:

	LVMP	HVLP
Nozzle tip diameter	1.2–1.4 mm	1.2–1.4 mm
Inlet pressure	5–15 psi	5–15 psi
Air flow	10–15 SCFM	8.3 SCFM
Air cap	5–10 psi	5–10 psi

When using a pressure pot and agitator, keep the agitator at low mixing speed with air pressure of 20–50 psi. Use the lowest pressure necessary to keep the particles suspended.

Selective Coating

For higher volume applications, paint can be applied via selective coating equipment. Use a system with constant fluid recirculation to keep the particles from settling in the lines. A fluid nozzle ranging from 1.2 mm–1.4 mm diameter and 5–10 psi fluid pressure is recommended depending on nozzle size. Thin the paint to adjust the viscosity to the level appropriate for the valve being used.

Cure Instructions

Cure the paint in an oven at one of these time/temperature options:

Temperature	45 °C	65 °C	80 °C
Time	45 min	30 min	10 min

Clean-up

Clean the spray system and equipment with tap water after use.

Storage and Handling

Store between 4 and 40 °C in a dry area, away from sunlight (see SDS).

Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.